

## CLAIMS

- [1] A resin sheet, characterized in that it comprises a cured resin layer containing in a resin a glass fiber cloth-like material and inorganic particles, and  
5 is structured to have a haze value of 10% or lower.
- [2] A resin sheet according to claim 1, wherein a refractive index difference between a resin that forms the cured resin layer, and the glass fiber cloth-like material is 0.01 or less.
- [3] A resin sheet according to any one of claims 1 and 2, wherein the amount  
10 of the inorganic particles contained in the cured resin layer is 15 to 60 wt. %.
- [4] A resin sheet according to any one of claims 1 to 3, wherein the inorganic particles are silica particles.
- [5] A resin sheet according to any one of claims 1 to 4, wherein the resin that forms the cured resin layer is an epoxy resin.
- 15 [6] A resin sheet according to any one of claims 1 to 5, whose coefficient of linear expansion is equal to or less than  $5.0 \times 10^{-5}/^{\circ}\text{C}$  at 25 to 160°C.
- [7] A resin sheet according to any one of claims 1 to 6, whose light transmittance is 88% or more.
- [8] A resin sheet according to any one of claims 1 to 7, wherein a gas barrier  
20 layer is further laminated.
- [9] A resin sheet according to any one of claims 1 to 8, wherein a hard-coat layer is further laminated.
- [10] A liquid crystal cell substrate, characterized in that it comprises the resin sheet of any one of claims 1 to 9.
- 25 [11] A liquid crystal display device, characterized in that it comprises the liquid crystal cell substrate of claim 10.
- [12] A substrate for an electroluminescence display device, characterized in

that it comprises the resin sheet of any one of claims 1 to 9.

[13] An electroluminescence display device, characterized in that it comprises the substrate for an electroluminescence display device of claim 12.

[14] A substrate for a solar cell, characterized in that it comprises the resin  
5 sheet of any one of claims 1 to 9.